


Pressure/Temperature Ratings


Class 150 Flanged, Butt Weld

Cold Working Pressure (PSIG)	
Carbon Steel – WCB	285
Stainless Steel – CF8M, CF3M	275
Alloy 20 – CN7M	230
Monel M-35-1	230
Hastelloy CW-6M	290
Titanium – B367 Gr C3	265



Class 150-300 Screwed, Socket Weld Class 300 Flanged, Butt Weld


Cold Working Pressure (PSIG)	
Carbon Steel – WCB	740
Stainless Steel – CF8M, CF3M	720
Alloy 20 – CN7M	600
Monel M-35-1	600
Hastelloy CW-6M	750
Titanium – B367 Gr C3	695



Pressure/Temperature Ratings

Class 600 Flanged, Butt Weld Screwed, Socket Weld

Cold Working Pressure (PSIG)	
Carbon Steel – WCB	1480
Stainless Steel – CF8M, CF3M	1440
Alloy 20 – CN7M	1200
Monel M-35-1	1200
Hastelloy CW-6M	1500
Titanium – B367 Gr C3	1390



Note: Consult factory for pressure/temperature recommendations for 3" and larger Class 600 fire-safe seats.